

23. DEZ. 2004 11:07 ignatio... ZWISGLE GMBH RT +49 7121 509325

NR. 3168 S. 2

An American National Standard

Standard Method for GRADING COTTON YARNS FOR APPEARANCE^{1, 2}

This standard is issued under the fixed designation D 2255; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval.

INTRODUCTION

Cotton yarn appearance standards were first adopted in 1938 and revised in 1964, with Series III being revised again in 1975. The 1964 boards had different yarn sizes for the four-grade exhibits on each board. The 1975 Series III board used the same yarn number for each grade.

The appearance grade of yarn is based on the composite evaluation of several factors, such as unevenness, fuzziness, and neppiness. The differences in the yarn numbers in the 1964 standards along with the differences in other factors distort the comparison between grades and makes grading more difficult.

To overcome this shortcoming, in 1975 the Series III board was revised using the same size yarn for all four grades. After evaluating the improvements, it was decided to revise all of the series using a mid-range yarn number for each grade in the series, and narrow the range in the most active series. This was accomplished by adding a new board, Series VI. A near mid-range yarn number was selected to represent equal steps between adjacent grades for all the factors considered in yarn appearance grading. These yarns were produced with current commercial manufacturing equipment and practices.

Finally, in order to obtain better yarn definition and better reproducibility from set to set, it was decided to use offset photo printing.

1. Scope

1.1 This method covers the grading of cotton yarns for appearance. The method is applicable to all single cotton yarns, whether carded or combed. It may also, by agreement, be used for grading yarns made from mixtures of cotton with other fibers.

1.2 This method does not apply to plied yarns, to yarns made from fibers other than cotton, nor (except by agreement) to yarns spun from mixed fibers.

2. Applicable Documents

2.1 ASTM Standards:

D 123 Definitions of Terms Relating to Textiles³

D 2258 Practice for Sampling Yarn for Testing³

3. Definitions

3.1 *yarn appearance, n.*—the visual effect obtained by viewing a sample wound with a designated traverse on a black board of designated size.

3.2 *thick place, n.*—a yarn defect characterized by a diameter greater than that of the adjoining segments and extending for ¼ in. (6 mm) or more.

¹ This method is under the jurisdiction of ASTM Committee D-13 on Textiles and is the direct responsibility of Subcommittee D13.58 on Yarn Test Methods, General.

Current edition approved June 29, 1979. Published August 1979. Originally published as D 2255 - 64. Last previous edition D 2255 - 75.

² The requirements for the appearance of cotton yarns are covered in Tolerances D 2645, Roller-Drafted Yarns.

³ Annual Book of ASTM Standards, D 13.58.

23 DEC 2004 11:03

ZWEIGLE CMBH RT #49 7121 509325

NR 3158 S. 3

3.2.1 The unevenness is normally caused by a greater number of fibers per yarn cross section than usual.

3.3 *thin place, n.*—a yarn defect characterized by a segment that is substantially (at least 25 %) smaller in diameter than the average diameter of the yarn.

3.3.1 A thin place may be of any length.

3.4 *bunch, n.*—a defect in a yarn characterized by a segment not over ¼ in. (6 mm) in length that shows an abrupt increase in diameter caused by more fibers matted in this particular place. (*Syn.* slug, slub).

3.5 *nep, n.*—in cotton, a defect in yarn, or card sliver, characterized by one or more fibers occurring in a tangled unorganized mass.

3.5.1 The fibers may be tangled because they were not straightened during carding and subsequent processing operations, or the fibers may be adhering to a bit of foreign material such as wax or a piece of seed coat.

3.6 *cover, n.*—in yarns, the outside layer of fibers that form the surface.

3.7 *fuzz, n.*—untangled fiber ends that protrude from the surface of a yarn.

3.7.1 Fuzz should not be confused with "cover."

3.8 For definitions of other textile terms used in this method, refer to Definitions D 123.

4. Description of Yarn Grades

4.1 *Grade A Yarn*—Grade A yarn may have no large neps which are over three times the normal diameter of the yarn and very few small ones. Grade A yarn must have good uniformity from inch to inch, and good cover without excessive fuzziness. No leaf nor other foreign matter may be present in Grade A yarn.

4.2 *Grade B Yarn*—Grade B Yarn may have no large neps, but may have a few small ones. Grade B yarn may have no more than three small pieces of foreign matter per board or specimen providing they do not form slugs. Grade B yarn may be slightly more irregular and may have slightly more fuzz than a Grade A yarn.

4.3 *Grade C Yarn*—Grade C yarn may have more neps, and larger ones as well as more fuzziness and a greater amount of foreign matter than Grade B yarn. The contrast between the thick and thin places and the normal diameter of the yarn may be greater than in

Grade B yarn resulting in an over-all rougher appearance.

4.4 *Grade D Yarn*—Grade D yarn may have some slubs that are more than three times the average diameter of the yarn. Grade D yarn may have more neps, neps of a larger size, more thick and thin places, more fuzz and more foreign matter than Grade C yarn. When slubs or large neps are present, Grade D yarn may have fewer neps than Grade C yarn. Grade D yarn may have an over-all rougher appearance than Grade C yarn.

4.5 *Yarn Below Grade D*—Yarn below Grade D may have more defects and an overall rougher appearance than Grade D yarn.

NOTE 1—The permitted number of defects for any grade should always be determined by comparison with the official "ASTM Cotton Yarn Appearance Standards" photographs.

5. Summary of Method

5.1 This method is considered satisfactory for acceptance grading of commercial shipments because it has been used extensively in the trade for this purpose. In case of dispute, the statistical bias, if any, between the laboratory of the purchaser and the laboratory of the seller should be determined with each comparison being based on testing randomized specimens from one sample of material.

5.2 Yarn specimens, wound on black boards, are compared with photographs of specimens representing the appearance grades. The grade is based on fuzziness, neppiness, unevenness, and visible foreign matter.

6. Uses and Significance

6.1 The appearance of a woven or knitted fabric depends to a large extent on the smoothness, cleanliness, and general appearance of the yarns from which it is manufactured. Instruments are available for the measurement of unevenness and for counting neps and other imperfections, but the values obtained from such tests are not easily integrated into an over-all expression for actual appearance. Yarn appearance grading affords additional information which the manufacturer of woven or knitted goods may, through experience, correlate with the appearance to be expected in fabrics made from the yarns.

23. DEZ. 2004 11:03

ZWEIGLE GMBH RT +49 7121 509325

NR. 3186 S. 4

4511 D 2255

7. Apparatus

7.1 Yarn Appearance Standards⁴—A series of photographic standards representing Grades A, B, C, and D in six ranges of yarn numbers. Grade A is the highest and the others are progressively lower. The range of yarn numbers to be graded by each series is listed in Table 1. Each photograph is 140 by 240 mm in size, and the four photographs of each series are mounted on a 350 by 650-mm panel. The standards are illustrated in Fig. 1.

7.2 Yarn Grading Cabinet⁵—A cabinet with storage space for the appearance standards, a shelf or rack on which one panel of standards and the specimen to be graded can be displayed, and lights mounted on brackets so as to illuminate the specimen and standards at the proper angle. A picture of the yarn appearance grading cabinet being used by a grader is shown in Fig. 2.

7.2.1 The lights on the cabinet shall consist of two units focused on the standard when in the grading position from a location about 300 mm in front with one unit slightly above and one unit slightly below the standards. Each unit shall be equipped with either two 150-W daylight incandescent bulbs or one 20-W daylight fluorescent tube mounted in a reflector which extends across the cabinet to provide uniform light intensity over the standard.

7.3 Yarn Boards—Rectangles of heavy cardboard, wallboard, or light plywood, at least 140 by 250 mm in size, finished completely in dull black. To fit the usual type of winder, there should be a rounded 20-mm notch at the center of one of the long edges to accommodate the screw of the revolving clamp. In one of the short edges there should be knife cuts or small notches to hold the ends of the yarn. One of these should be placed approximately 10 mm from the straight side of the board and the other about 20 mm from the notched side.

7.4 Yarn Board Winder⁶—A small machine to rotate a yarn board end-over-end, and fitted with a traversing guide to advance the yarn across the board as it is wound. The machine shall be capable of spacing the yarn evenly as required in Table 1 with a tolerance of $\pm 10\%$.

7.4.1 All parts of the tension device on the winder which comes in contact with the yarn shall be made of a smooth material, such as porcelain or metal, to prevent disturbance of

the fibers in the yarn.

8. Adjustment of Yarn Board Winder

8.1 Set the traversing mechanism of the winder for the required spacing, wind a trial board, and count the wraps in a width of at least 25 mm. If the number of wraps does not conform to the tolerances specified in Table 1, adjust to the correct spacing (Note 2). On the most generally used type of machine, this adjustment may be made by changing the diameter of the friction wheel or by filing a new notch in the shaft on which the friction wheel slides.

NOTE 2—The spacing is critical in its influence on the appearance of the specimen. Closer spacing places a greater length of yarn on the board and hence, a larger number of imperfections per unit of area. Wider spacing has the opposite effect.

9. Sampling, Selection, and Number of Specimens

9.1 Take the bulk sample as specified in the applicable material specifications or in accordance with Practice D 2258.

9.2 For the laboratory sample, take five packages (cones, spools, bobbins, etc.) at random from each case of the bulk sample.

9.3 Prepare one specimen from each package in the laboratory sample.

10. Conditioning

10.1 Specimens need be neither preconditioned nor conditioned.

11. Preparation of Specimens

11.1 Mount a yarn board in the revolving clamp of the winder and set the traversing mechanism to give the spacing specified in Table 1 for the nominal yarn number.

11.2 If it is desired to compare two or more lots differing slightly in yarn number so that

⁴ Available from the American Society for Testing and Materials, 1916 Race St., Philadelphia, Pa. 19103. Request Adjunct No. as follows:

12-422551-18 (Series 1-79)	12-422554-18 (Series 4-79)
12-422552-18 (Series 2-79)	12-422555-18 (Series 5-79)
12-422553-18 (Series 3-79)	12-422556-18 (Series 6-79)

⁵ Prints of detailed drawings of a suitable cabinet are available at a nominal cost from the American Society for Testing and Materials, 1916 Race St., Philadelphia, Pa. 19103. Request Adjunct No. 12-422550-00.

⁶ A card winder similar to the one described may be obtained from the Alfred Suter Co. 200 Fifth Ave., New York, N. Y. 10010.

23 DEC 2004 11:08 ZWEIGLE GMBH RT +49 7121 509325
they fan the different series (except for the 7s), wind them to the same spacing and compare with the same series of standards. In any case, compare only yarns the numbers of which are not more than 10 % above the upper limit or more than 10 % below the lower limit of the series of standards by which they are graded.

11.3 Mount the package so that it unwinds freely, lead the yarn through the tension device and traversing pigtail guide, and secure the end in a notch or knife-cut near the left hand side of the board. When unwinding yarn over the end of the package, wind the board at 50 to 100 rpm using just sufficient tension to space the yarn evenly on the board. If the package must be unwound from the side, wind at a low enough speed to avoid jerking, breaking, or tangling the yarn.

11.4 Wind until the last wrap is within approximately 20 mm of the right-hand side and secure the end of the yarn near the right-hand corner.

12. Procedure

12.1 Place the appropriate series of ASTM Cotton Yarn Appearance Standards in the grading position on the shelf or support in the yarn grading cabinet. Set one specimen at a time in front of the panel of standards and move it from side to side for comparison with the different standards from about 1 m.

12.2 Thick places, bunches, slubs, or slugs are considered the worst defects of yarn because in practically all cases they will cause end breakage in later processing. Yarn with bunches, slubs, or slugs will not be assigned Grade A or Grade B.

12.3 When any one defect or combination of them is excessive for a grade, assign the next lower grade to the specimen.

12.4 Assign to the specimen the grade designated for the photograph which it is equal to or better than without being equal to the next higher grade. Consider the information in Section 4 in making the assignment. Also, grade the back of the specimen in a similar manner. Record the grade of the poorer side as the grade of the specimen if the two sides are as much as one grade different.

12.5 Each specimen shall be graded independently by three experienced yarn graders, and the grade reported shall be that assigned

by the three graders when they are in agreement, or by two in agreement, provided the third grader does not differ by more than one grade from the grade assigned by the other two. When the range of the grades assigned by the three graders to a specific specimen is greater than one, the three graders shall review the specimen in conference and agree on the grade to be assigned, or if they cannot agree the specimen shall be rejected.

12.6 For acceptance grading of commercial shipments, recognize only the five grades: A, B, C, D, and Below Grade D. If 80 % of the specimens graded are equal to or better than the specified grade, and the remaining 20 % do not fall below the next lower grade (as based on many years of commercial grading experience), consider the lot as meeting cotton yarn appearance specifications.

12.7 For quality control or research purposes, the grader may assign "plus" grades to specimens that are intermediate in appearance between one grade and the next higher grade.

13. Calculation

13.1 In acceptance testing, if no specimen falls more than one grade below that specified, determine the percentage of specimens that are equal to or better than the specified grade. If one or more specimens fall more than one grade below that specified, reject the lot.

13.2 For research or experimental purposes, it may be desired to compare the average quality of different lots of yarn. In this case, convert the yarn appearance grade of each specimen to its equivalent yarn appearance given in Table 2 and calculate the average yarn appearance index.

14. Report

14.1 State that the specimens were tested as directed in ASTM Method D 2255. Describe the material or product sampled and the method of sampling used.

14.2 Report the following information:

14.2.1 Grade of the poorest specimen in the lot,

14.2.2 Grade equalled or exceeded by at least 80 % of the specimens.

14.2.3 Average yarn appearance index, if determined.

14.2.4 Nominal yarn number,

14.2.5 Wrap spacing, and

14.2.6 Series of Cotton Yarn Appearance

23. DEC. 2004 11:09

ZWEIGLE CMDB RT 449 7121 509325

NR. 3168 S. 6

97117 U 2255

Standards used for grading, for example, Series 3-79.

15. Precision

15.1 Experienced yarn graders working independently agree on the grade of about 67 % of the specimens and seldom differ by more than one grade on the remaining 33 %.

15.2 The averages of the grades assigned by three experienced yarn graders will agree on about 90 % of the specimens and will not differ by more than one grade for the remaining 10 %.

15.3 The precision data in 15.1 and 15.2 are based on commercial grading as stated in 12.6.

TABLE 1 Requirements for Preparations of Specimens

Series	Range of Yarn Numbers		Count ^A	Wraps ^B	
	Single Cotton Count	Tex		per in.	per cm
1	1 to 12	590 to 50+	8	20	8
2	12+ to 24	50 to 25+	18	20	8
3	24+ to 36	25 to 16+	30	22	9
4	36+ to 50	16 to 12+	42	32	13
5	50+ to 75	12 to 8+	60	38	15
6	75+ to 135	8 to 4+	100	48	19

^A Actual single yarn count used on boards.

^B The specified number of wraps is subject to a tolerance of ± 10 %.

TABLE 2 Yarn Appearance Indexes

Grade	Index
A and above	130
B+	120
B	110
C+	100
C	90
D+	80
D	70
Below D	60



FIG. 1 ASTM Cotton Yarn Appearance Standards.

23. DEC. 2004 11:09

ZWEIGLE CMBH RT +49 7121 509325

NR. 3169-18. 7




FIG. 2 Yarn Appearance Grading Cabinet Being Used by Grader.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 1916 Race St., Philadelphia, Pa. 19103, which will schedule a further hearing regarding your comments. Failing satisfaction there, you may appeal to the ASTM Board of Directors.

zweigle

Zweigle Textilprüfmaschinen GmbH & Co. I
Ferdinand-Lassalle-Straße 54
D-72770 Reutlingen



16.12.2004


Schlafhorst Effekt- OE-1(1. Segment)

Winding density : 8.00 per cm
Yarns : Schlafhorst Effekt-OE_

Zweigle Textilprüfmaschinen GmbH & Co. I
Ferdinand-Lassalle-Straße 54
D-72770 Reutlingen



zweigle




16.12.2004


Schlaflorst Effekt-OE-2(2. Segment)

Winding density : 8.00 per cm
Yarns : Schlaflorst Effekt-OE_

Zweigle Textilprüfmaschinen GmbH & Co. I
Ferdinand-Lassalle-Straße 54
D-72770 Reutlingen



zweigle



16.12.2004


Schlaflhorst Effekt-OE-3(3. Segment)

Winding density : 8.00 per cm
Yarns : Schlaflhorst Effekt-OE_

Zweigle Textilprüfmaschinen GmbH & Co. I
Ferdinand-Lassalle-Straße 54
D-72770 Reutlingen



zweigle




16.12.2004

Schlafhorst Effekt-OE-4(4. Segment)

Winding density : 8.00 per cm
Yarns : Schlafhorst Effekt-OE_


Sheet 1 of 2

Join here →



Sheet 2 of 2

← Join here



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.